### Conformal Coatings

# Technical Data Sheet





### 2K550

## **Two-Component Polyurethane Coating**

2K550 is a flame retardant, tough yet flexible, high performance two-component, solvent-free conformal coating, designed specifically for selective coating processes. 2K550 is characterised by greater coating thickness and enhanced edge coverage and shows improved adhesion, hardness and scratch and solvent resistance when compared to conventional single component coatings.

- Flame retardant at thicknesses below 350µm; meets UL94 V-0
- Excellent resistance to humidity, condensation and immersion in water
- · Coating exhibits excellent adhesion and hardness; low stress during automotive thermal shock cycles
- High coating thickness achievable; enhanced edge coverage

Approvals RoHS Compliant (2015/863/EU): Yes

REACH Compliant: Yes

IPC-CC-830 Rev. C: Meets Requirements
UL746 Meets UL94 V-0

Liquid Properties Appearance: Opaque Black Liquid

Density @ 20°C (g/ml): 1.46 (mixed)
Flash Point: >100°C
Min. Solids Content (1hr @ 80°C): >99%
Mix Ratio: 2:1 v/v

Mix Ratio: 2:1 v/v

Mixed System Viscosity @ 25°C: Sprayable

Useable Life @ 20°C: 180 Minutes

Touch Dry Time at 20°C: 240 Minutes

Recommended Drying Time: 10 Minutes @ 80°C

Recommended brying time.

**Dry Film Coating** Colour: Opaque Black

Recommended Coating Thickness: 100-300μm
Temperature Range: -40 to +130°C
Thermal Shock Range: -65 to +125°C\*

Thermal Shock (1000 cycles): No cracking, blistering or delamination\*

Shore Hardness: A95
Dielectric Strength: 90 kV/mm
Surface Insulation Resistance:  $1 \times 10^{15} \Omega$ Moisture Resistance (IPC-CC-830): 9.24 x  $10^9 \Omega$ Flammability: Meets UL94 V-0

\*Other thermal shock regimes are also possible, i.e. different temperatures, number of cycles, etc.

#### Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way, Ashby de la Zouch, Leicestershire LE65 1JR T +44 (0)1530 419 600 F +44 (0)1530 416 640 BS EN ISO 9001:2008 Certificate No. FM 32082





<u>Description</u>	<u>Packaging</u>	Order Code
2K550 Conformal Coating Part A	5 Litre	E2K5505L
2K Part B 1L	1 Litre	E2KPBO01L
2K Part B 5L	5 Litre	E2KPBO05L

#### **Directions for Use**

2K550 is intended to be applied by selective spray coating. It is recommended that the use of a high accuracy, volumetric metering system, such as progressive cavity pumps are used to control the mix ratio of the two components. It is recommended that a minimum 10 turn static mixer is used to ensure complete mixing of the two components prior to reaching the dispense valve. The use of a heated applicator block can result in reduced film builds and faster cycle times. 60°C is a typical set-point.

The material works best when a relatively high flow rate and low atomising air combination is used, but this will depend on the design of the assembly, required cycle times and other process considerations. Machine settings for various 2K selective spraying options are available upon request.

### Inspection

2K550 contains a UV trace, which allows inspection of the PCB after coating to ensure complete and even coverage; the stronger the reflected UV light, the thicker the coating layer is. UV light in the region of 375nm should be used for inspection. 2K550 is also opaque black in colour, further facilitating visual inspection and improving contrast for Automated Optical Inspection Systems.

Revision 5: Apr. '19