



# MOLYKOTE® 41 Extreme High Temperature Bearing Grease

Silicone grease that can be used at temperatures higher than those of normal silicone greases

## Features

- Does not melt, even at high temperatures
- Superior thermal stability
- Superior oxidation resistance
- Water-resistant

## Composition

- Silicone oil
- Carbon black
- Corrosion inhibitor

## Applications

Ideal for use in oven conveyors, kiln dollies, molten salt evacuation pumps, steam turbine regulator links, knife-edge power breakers, etc.

## How to use

Clean points of application. As is usual with lubricating greases, apply or fill by means of a brush, spatula, or automatic lubrication device.

Do not use on painted surfaces. Do not use on steel bearing under high loads.

## Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

## Usable life and storage

When stored, unopened, in a cool, dark place, this product has a usable life of 60 months from the date of production.

## Packaging

This product is available in 1 kg cans.

## Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard <sup>(1)</sup>	Test	Unit	Result
	Appearance		Black
	Base oil viscosity at 25°C	mm <sup>2</sup> /s	316
JIS K 2220	Penetration (worked 60 times)	mm/10	260 to 300
	NLGI class		2
	Service temperature range	°C	-20 to 290
	Density	g/cm <sup>3</sup>	1.1
JIS K 2220	Drop point	°C	None
MIL S 8660	Bleed (150°C/24 hours)	%	4.0
MIL S 8660	Evaporation (150°C/24 hours)	%	1.0
JIS K 2220	Water washout (38°C/1 hour)	%	0.5
ASTM D2596	Four ball weld load (1,500 rpm/1 minute)	N	1,500
	Maximum Dn value	mm/minute	75,000

<sup>(1)</sup>JIS: Japanese Industrial Standard. ASTM: American Society for Testing and Materials. MIL: Military Specification and Standards.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.*  
© 2002-2021 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.