

# MOLYKOTE® D-96 UV Anti-Friction Coating

Air-curing dry-film lubricant with UV tracer

## Features & benefits

- Excellent “anti-squeak” performance
- Low coefficient of friction
- Constant coefficient of friction at different temperatures
- Water-based
- Does not contain NMP and APEO
- Transparent coating
- Dry film detectable with UV light

## Composition

- Solid lubricants
- Organic binder
- Water
- Stabilizer
- UV tracer

## Applications

Helps to eliminate noise on interior automotive components such as door panels, decorative trims, arm rests, central consoles, dashboards, glove boxes, etc., as well as leather equipment. Suitable for material combinations such as car paint/plastic, plastic/plastic, plastic/metal, car paint/leather, plastic/leather, leather/leather with slow movements or vibrations at low loads.

## How to use

### Surface preparation

First, clean and degrease the surface that will be coated with MOLYKOTE® D-96 UV Anti-Friction Coating.

### How to apply

Stir MOLYKOTE® D-96 UV Anti-Friction Coating thoroughly before applying by spraying, dip-spinning or brushing.

Recommended dry-film thickness: 5 to 20 µm.

### Curing

After 10 minutes at room temperature (23°C, 73°F), the wet film of MOLYKOTE® D-96 UV Anti-Friction Coating is touch-dry and the coated parts can be handled; the drying time can be reduced to 2 minutes with hot air at 60/80°C (140/176°F); after 120 minutes at 23°C (73°F), the dry film is fully cured and it can be fully loaded.

## Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard <sup>(1)</sup>	Test	Unit	Result
	Color (dry film)		Transparent
	Service temperature range	°C	-40 to 150
		°F	-40 to 302

Physical properties			
DIN EN ISO 2431	Viscosity at 23°C (73°F) cup #4	s	41
ASTM D1475	Density at 23°C (73°F)	g/ml	1.32

Anti-noise			
VDA 230-206	Anti-noise tester, speed 2 mm/s, temperature 23°C (73°F), rel. humidity 40%, load: 20 N, 10,000 cycles		
	<i>Material pairing:</i>	<i>RPN<sup>(2)</sup></i>	<i>Noise</i>
	Car paint vs PVC foil 1 mm thick	1	None
	PC-ABS vs PVC foil 1 mm thick	1	None

Coefficient of friction (µ)			
	Anti-noise tester, speed 2 mm/s, temperature 23°C (73°F), rel. humidity 40%, load 20 N		
	<i>Material pairing:</i>	<i>µ-static</i>	<i>µ-dynamic</i>
	Car paint vs PVC foil 1 mm thick	0.31	0.21
	PC-ABS vs PVC foil 1 mm thick	0.23	0.14
	Oscillating tester, speed 10 mm/s, load 2 N, temperature 23°C (73°F), rel. humidity 40%, material pairing:	<i>µ-static</i>	<i>µ-dynamic</i>
	POM ball vs PVC foil 1 mm thick	0.41	0.156
	POM ball vs TPO foil 1 mm thick	0.34	0.104

<sup>(1)</sup>DIN: Deutsche Industrie Norm. ISO: International Standardization Organization. ASTM: American Society for Testing and Materials. VDA: Verband der Automobilindustrie.

<sup>(2)</sup>RPN: Risk priority number.

### **Thinner**

MOLYKOTE® D-96 UV Anti-Friction Coating is ready to use for spraying; thinning (viscosity adjustment) can be carried out by using distilled water or tap water. Water or a mixture of DPM (CAS # 34590-94-8) or TPM (CAS # 25498-49-1) in water (up to 20%) can be used for cleaning the application equipment components.

### **Coverage**

When applied at 12 µm dry-film thickness, MOLYKOTE® D-96 UV Anti-Friction Coating has a coverage of approx. 20 m<sup>2</sup>/kg (this value does not take into account the losses generated during the application process).

### **Handling precautions**

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

### **Usable life and storage**

When stored at 23°C (73°F) in the original unopened containers, this product has a usable life of 12 months from the date of production.

### **Packaging**

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.  
© 2016-2019 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.